

Altuglas® HT 121

Polymethyl Methacrylate Acrylic
Altuglas International of Arkema Inc.



Prospector

General

Material Status	• Commercial: Active
Availability	• Europe
Forms	• Granules
Multi-Point Data	• Specific Volume vs Temperature (ISO 11403-2) • Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value Unit	Test Method
Density	1.19 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.0 g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20 to 0.60 %	ASTM D955
Water Absorption (Equilibrium, 23°C, 50% RH)	0.40 %	ISO 62

Mechanical	Nominal Value Unit	Test Method
Tensile Stress (Yield, 23°C)	70.0 MPa	ISO 527-2
Tensile Strain (Break, 23°C)	5.0 %	ISO 527-2
Flexural Modulus (23°C)	3450 MPa	ISO 178
Flexural Strength (23°C)	103 MPa	ISO 178
Compressive Stress (23°C)	117 MPa	ISO 604

Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.0 kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength (23°C)	11 kJ/m ²	ISO 179/2U
Notched Izod Impact Strength (23°C)	1.80 kJ/m ²	ISO 180/1A

Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (M-Scale)	102	ASTM D785

Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature 0.45 MPa, Unannealed	119 °C	ISO 75-2/B
1.8 MPa, Unannealed	110 °C	ISO 75-2/A
Vicat Softening Temperature	121 °C	ISO 306/B
CLTE - Flow (-30 to 23°C)	0.000065 cm/cm/°C	ASTM D696
Specific Heat	2090 J/kg/°C	
Thermal Conductivity (23°C)	0.22 W/m/K	

Electrical	Nominal Value Unit	Test Method
Surface Resistivity	> 1.0E+14 ohms	ASTM D257
Volume Resistivity	> 1.0E+15 ohm·cm	ASTM D257
Dielectric Strength	20 kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.70	ASTM D150
Dissipation Factor (1 MHz)	0.040	ASTM D150

Flammability	Nominal Value Unit	Test Method
Flame Rating - UL	HB	UL 94

Optical	Nominal Value Unit	Test Method
Refractive Index ²	1.490	ISO 489
Transmittance	92.0 %	ASTM D1003
Haze	0.50 %	ASTM D1003

Injection	Nominal Value Unit
Drying Temperature	90.0 to 100 °C
Drying Time	4.0 to 6.0 hr
Processing (Melt) Temp	240 to 250 °C
Mold Temperature	80.0 to 90.0 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method B

